



American Concrete Institute
Always advancing

ERRATA as of October 6, 2021
CP-1, 40th Edition
Technician Workbook for
Concrete Field Testing Technician—Grade I
First Printing
Reported by ACI Certification Programs Committee

Note the following corrections, in red:

p. 20: Sampling Fresh Concrete

	Max. Size	Wet Sieve Size
Slump	1-1/2 in. [37.5 mm]	1-1/2 in. [37.5 mm]
Air Content (<i>Pressure</i>)	2 in. [50 mm]	1-1/2 in. [37.5 mm]
Air Content (<i>Roll-A-Meter</i>)	1-1/2 in. [37.5 mm]	1 in. [25 mm]
Cylinders (<i>6 x 12 in. [150 x 300 mm]</i>)	2 in. [50 mm]	2 in. [50 mm]
Cylinders (<i>4 x 8 in. [100 x 200 mm]</i>)	1-1/4 in. [31.5 mm]	1-1/4 in. [31.5 mm] N/A

Table 1.1—Maximum Aggregate Size